

### PRODUCT DESCRIPTION

Stonchem 620 is a highly cross-linked, novolac epoxy, conductive and spark-proof lining system applied at a nominal thickness of 3.3 mm. One trowel-applied mortar layer provides a heavy-duty, conductive and non-sparking chemical barrier for moderate traffic areas with no thermal shock or cracking. Stonchem 620 is the ideal lining surface for solvent storage and other areas where an explosion is a potential from sparking. When tested using ESD S7.1 test method, this carbon based system measures a resistance lower than 1,000,000 ohms. Stonchem 620 has excellent resistance to concentrated sulfuric acid, solvents and caustics.

### USES, APPLICATIONS

- Secondary Containment Areas
- Solvent Storage Rooms
- Drum Storage Areas
- Pump Pads and Pedestals
- Explosion Rooms

### PRODUCT ADVANTAGES

- Excellent chemical resistance to most mineral acids, solvents and all caustics
- Factory-proportioned units for easy application
- Conductive and non-sparking

### CHEMICAL RESISTANCE

Stonchem 620 is formulated to resist a variety of chemical solutions. Refer to the Stonchem 600 Series Chemical Resistance Guide, which lists reagent concentration and temperature recommendations for each product.

### PACKAGING

Stonchem 620 is packaged in units for easy handling. Each unit consists of:

#### **Mortar**

2 cartons of Stonchem 600/620 Liquids

A carton contains:

- 4 foil bags of amine
- 4 poly bags of resin

8 bags of 620 Mortarcoat aggregate

#### **Topcoat**

1 carton of Stonchem 620 Series Topcoat

A carton contains:

- 2 foil bags of amine
- 2 cans of resin

### COVERAGE

Each unit of Stonchem 620 will cover approximately 16.72 m<sup>2</sup> at a thickness of 3.3 mm.

**Note:** Coverage rates shown are theoretical. Actual coverage rates may vary. Make necessary allowances for the condition of the surface to be coated, working conditions, waste, spillage, experience level and skill of the installers, etc.

### STORAGE CONDITIONS

Store all components between 10 to 24°C in a dry area. Keep out of direct sunlight. Avoid excessive heat and do not freeze. The shelf life is 3 years in the original, unopened container.

### SUBSTRATE

Stonchem 620, with appropriate primer, is suitable for application over concrete and the following uncoated newly-applied Stonhard mortars and grouts: GS, HT, UR, UT, TG6, TG8, CR5 and PM5. For questions regarding other possible substrates or an appropriate primer, contact your local Stonhard representative or Technical Service.

### PHYSICAL CHARACTERISTICS

Compressive Strength.....	96.5 N/mm <sup>2</sup>
(ASTM C-579)	
Tensile Strength.....	13.8 N/mm <sup>2</sup>
(ASTM D-638)	
Flexural Strength.....	44.8 N/mm <sup>2</sup>
(ASTM C-580)	
Flexural Modulus	
of Elasticity.....	12.8 x 10 <sup>3</sup> N/mm <sup>2</sup>
(ASTM C-580)	
Hardness.....	85 to 90
(ASTM D-2240, Shore D)	
Abrasion Resistance.....	0.07 gm max. weight loss
(ASTM D-4060, CS-17)	
Thermal Coefficient	
of Linear Expansion.....	2.2 x 10 <sup>-5</sup> m./mm.°C
(ASTM C-531)	
Color.....	Black
Cure Rate.....	4 to 6 hours tack-free
(@21°C)	
VOC.....	Stonchem 620 Topcoat 68 g/l
.....	Stonchem 600/620 Liquids 20 g/l
(ASTM D-2369, Method E)	

**Note:** The above physical properties were measured in accordance with the referenced standards. Samples of the actual system, including binder and filler, were used as test specimens.

## SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service.

## APPLICATION GUIDELINES

For optimal working conditions, substrate temperature must be between 15 to 27°C. Cold areas must be heated until the slab temperature is above 13°C to ensure the material achieves a proper cure. A cold substrate will make the material stiff and difficult to apply. Warm areas or areas in direct sunlight must be shaded or arrangements made to work during evenings or at night. A warm substrate (15 to 27°C) will aid in the material's workability; however, a hot substrate (27 to 37°C) or a substrate directly in the sun will shorten the material's working time and can cause other phenomenon such as pinholing and bubbling. Substrate temperature must be greater than 3°C above dew point during application and curing period.

Application and curing times are dependent upon ambient and surface conditions. Consult Stonhard's Technical Service Department if conditions are not within recommended guidelines.

## APPLYING

### Priming

Vacuum before priming and make sure the substrate is dry. The use of Stonchem Epoxy Primer is necessary in all applications of Stonchem 620. This ensures maximum product performance. (See the Stonchem Epoxy Primer product data sheet for details.)

**Note:** The Stonchem Epoxy Primer must remain tacky during installation of the Mortar.

### Mortar

Empty the amine and resin into a c.a. 20 liter mixing bucket. Put the container on a J.B. Blender and pre-mix for one minute. When the pre-mixing is complete, set the J.B. Blender for 90 seconds. Start the J.B. Blender and gradually add the Mortar aggregate. The mixed mortar should be free of any clumping. Apply the mortar onto the substrate by pouring the entire contents of the bucket onto the floor and screeding the mortar with a 12.5 mm x 12.5 mm V-notched trowel.

The entire contents of the bucket is now poured onto the floor, the material remaining in the bucket will settle. Additional mixing is required to remove the settled material from the bucket. Screed material immediately after it has been poured. Material allowed to settle on the substrate will be hard to screed. To achieve proper thickness of 3 mm, the trowel should be held at a 45 degree angle with notched tips in contact with the substrate at all times. Using a nap roller, roll the surface of the mortar until an even finish is achieved. Allow to cure for 4 to 6 hours.

**Note:** If the application requires a conductive system, you must test the mortar layer for conductivity using the megger to ensure it is within the proper range. The conductivity of the mortar layer must be below 500,000 ohms.

### Topcoat

Sand the mortar with a mechanical sander and sanding disc. Vacuum the area completely before applying Stonchem 620 Series Topcoat. Mix the Stonchem 620 Series Topcoat amine and epoxy in a c.a. 20 liter mixing container using a heavy-duty, slow-speed drill (400 to 600 rpm) with a Jiffy Mixer for 2 minutes. Pour the material onto the floor and spread using a 0.4 mm notched squeegee. Backroll the area with a medium nap roller to remove squeegee lines. When backrolling, use long roll strokes to decrease the visibility of roller lines. The wet film thickness of the coating is 250 to 300 microns.

Check the thickness with a wet film gauge. If the coating is too thick the conductivity readings will be effected.

**Note:** If the application requires a conductive system, you must test the finished system for conductivity using the megger to ensure it is within the proper range. The conductivity of the final system should be below 1,000,000 ohms. A static control report detailing the resistance readings over the entire area must be filled out and submitted to the customer.

## STATIC CONTROL PROPERTIES

Stonchem 620 has been specifically designed to comply with the ANSI/ESD S20.20 specification for the protection of electrical and electronic parts, assemblies and equipment.

<b>Surface Resistance</b> (ESD-S7.1)	< 1 megohms
<b>Body Voltage Generation</b> (ESD STM97.2)	< 100 volts*

*\*Body Voltage Generation is not solely a function of flooring conductivity but is a combination of many factors, including footwear and environmental conditions. Your specific environment and choice of footwear may yield slightly different results.*

Electrostatic Discharge (ESD) flooring has a variety of applications from microchip manufacturing to military ordinance. Therefore, each facility may have unique resistance requirements based on their individual ESD programs. It is important to identify the resistance requirements and test method used for each project prior to installing any ESD flooring.

## ELECTRICAL TESTING

Once the conductive mortar layer has cured, it must be tested for proper conductivity. Point-to-point and point-to-ground readings should be taken and all values should fall below  $5.0 \times 10^5$  ohms( $\Omega$ ).

The floor must also be tested after the carbon-filled topcoat has cured. Once the conductive sealer is tack-free, point-to-point and point-to-ground readings should be taken. All values must fall below  $1.0 \times 10^6$  ohms( $\Omega$ ).

**Note:** Stonhard tests all floors in accordance with the ESD S7.1 test method. Various other ESD standards and test methods are available and they each have their own unique parameters. Contact the Stonhard's technical service department if you wish to use a different test method.

## CURING

The surface of Stonchem 620 will be tack-free in 4 to 6 hours at 21°C. The area may be put back into service in 24 hours at 21°C. Ultimate physical and chemical characteristics will be achieved in 7 days.

## PRECAUTIONS

- Avoid contact with Stonchem 620 amine and resin, as they may cause skin, respiratory and eye irritation.
- Acetone is recommended for cleanup of Stonchem 600 amine and resin material spills. Use this material only in strict accordance with the manufacturer's recommended safety procedures. Dispose of waste materials in accordance with government regulations.
- The use of NIOSH/MSHA approved respirators using an organic vapor/acid gas cartridge is recommended.
- The selection of proper protective clothing and equipment will significantly reduce the risk of injury. Body covering apparel, safety goggles and impermeable nitrile gloves are highly recommended.
- In case of contact, flush the area with copious amounts of water for 15 minutes and seek medical attention. Wash skin with soap and water.
- If material is ingested, immediately contact a physician. **DO NOT INDUCE VOMITING.**
- Use only with adequate ventilation.

## NOTES

- Safety Data Sheets for Stonchem 620 are available online at [www.stonhard.com](http://www.stonhard.com) under Products or upon request.
- Specific information regarding chemical resistance is available in the Stonchem 600 Series Chemical Resistance Guide.
- A staff of technical service engineers is available to assist with product application or to answer questions related to Stonhard products.
- Requests for technical literature or service can be made through local sales representatives and offices, or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic and cleaning. Generally, high-gloss coatings are subject to a reduction in gloss, while matte-finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant buildup occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction-enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.

**CE MARKING**

The harmonized European Standard EN 1504-2 „Products and systems for the protection and repair of concrete structures – Definitions, requirements, quality control and evaluation of conformity – Part 2: Surface protection systems for concrete” gives specifications for products and systems based on methods “hydrophobic impregnation”, “impregnation” and “coating” for the various principles presented under EN 1504-9.

Products which fall under this specification have to be CE labelled as per Annex ZA. 1, Tables ZA1a to ZA 1g according to the scope and relevant clauses there indicated, and fulfill the requirements of the given mandate of the Construction Products Regulation nr. 305/2011. For flooring systems not dedicated to protect or reinstate the integrity of a concrete structure, EN 13813 applies. Products acc. EN 1504- 2 used as flooring systems with mechanical loads also must fulfil EN 13813. Here below indicated are the performance classes achieve according to the standard. For the specific performance results of the product to the particular tests, please see the actual values above in the PDS.

	
Stoncor Europe Rue du Travail 9 1400 Nivelles, Belgium 22	
DOP.620.2022.23.03 EN 1504-2	
Surface Protection Product Ingress Protection 1.3(C) Physical Resistance 5.1(C)	
Cap. Absorption & Permeability to Water Vapor	W<0.1 kg/m <sup>2</sup> *h <sup>0.5</sup>
Water Permeability	Class III
Permeability to CO <sup>2</sup>	S <sub>d</sub> >50m
Adhesion Strength by Pull-Off Test	>2.0 MPa
Fire Resistance	B <sub>f</sub> -s1
Abrasion Resistance	<3000mg, H-22
Impact Resistance	Class III

**IMPORTANT:**

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

Rev.03/22 EU  
 © 2022 Stonhard www.stonhard.com



**European Offices:**

Belgium	+32 674 93 710	Spain	+34 933 623 785	Germany	+49 240 541 740
France	+33 160 064 419	Portugal	+351 227 535 642	The Netherlands	+31 165 585 200
Poland	+48 422 112 768	United Kindom	+44 1925 649 458	Italy	+39 022 53 751
		East Europe	+48 422 112 768		