

### PRODUCT DESCRIPTION

Stonchem 626 is a highly cross-linked, novolac epoxy, conductive and spark-proof lining system applied at a nominal thickness of 1.5 mm. The resin, engineering fabric, mortarcoat, carbon-filled topcoat sequencing provides a smooth, heavy-duty, conductive and non-sparking chemical barrier which is resistant to small static cracks and moderate thermal shock. When tested using the ASTM F150 test method, this carbon-based system measures a resistance lower than 1,000,000 ohms. The Stonchem 626 system has excellent resistance to concentrated sulfuric acid, solvents and caustics.

### USES, APPLICATIONS

- Secondary Containment Areas/Tank Farms
- Concrete Sumps, Vaults and Trenches
- Pump Pads and Pedestals
- Storage Tanks
- Process Floors

### PRODUCT ADVANTAGES

- Excellent chemical resistance to most mineral acids, solvents and all caustic
- Engineering fabric aids in crack resistance
- Mortarcoat for added abrasion resistance
- Carbon-filled topcoat
- Factory-proportioned units for easy application
- Conductive and non-sparking

### CHEMICAL RESISTANCE

Stonchem 626 is formulated to resist a variety of chemical solutions. Refer to the Stonchem 600 Series Chemical Resistance Guide for lists of reagent concentrations and temperature recommendations.

### PACKAGING

Stonchem 626 is packaged in units for easy handling. Each unit consists of:

#### **Saturant**

1.25 cartons of Stonchem 600/620 Liquids

A carton contains:

- 4 foil bags of Amine
- 4 poly bags of Resin

#### **Engineering Fabric**

1 roll of Engineering Fabric 18.58 m<sup>2</sup> roll

#### **Mortarcoat**

0.75 carton of Stonchem 600/620 Liquids

A carton contains:

- 4 foil bags of Amine
- 4 poly bags of Resin
- 3 bags of Mortarcoat Aggregate

#### **Topcoat**

1 carton of Stonchem 620 Series Topcoat

A carton contains:

- 2 foil bags of Amine
- 2 cans of Resin

### COVERAGE

Each unit of Stonchem 626 will cover approximately 16.72 m<sup>2</sup> at an application thickness of 1.5 mm

**Note:** Coverage rates shown are theoretical. Actual coverage rates may vary. Make necessary allowances for the condition of the surface to be coated, working conditions, waste, spillage, experience level and skill of the installers, etc.

### STORAGE CONDITIONS

Store all components between 10 to 24°C in a dry area. Keep out of direct sunlight. Avoid excessive heat and do not freeze. The shelf life is 3 years in the original, unopened container.

### PHYSICAL CHARACTERISTICS

Tensile Strength.....	39 N/mm <sup>2</sup>
(ASTM D-638)	
Flexural Strength .....	101 N/mm <sup>2</sup>
(ASTM C-580)	
Flexural Modulus of Elasticity.....	5.5 x 10 <sup>3</sup> N/mm <sup>2</sup>
(ASTM C-580)	
Hardness .....	85 to 90
(ASTM D-2240, Shore D)	
Abrasion Resistance .....	0.12 gm max. weight loss
(ASTM D-4060, CS-17)	
Thermal Coefficient	
of Linear Expansion .....	2.1 x 10 <sup>-5</sup> m/mm°C
(ASTM C-531)	
Cure Rate .....	4 to 6 hours tack-free
(@21°C) .....	24 hours chemical service
VOC .....	600/620 Liquids - 20 g/l
(ASTM D-2369, Method E)	
.....	620 Series Topcoat - 68 g/l
Color .....	Black

**Note:** The above physical properties were measured in accordance with the referenced standards. Samples of the actual system, including binder and filler, were used as test specimens.

## SUBSTRATE

Stonchem 626, with appropriate primer, is suitable for application over concrete and the following uncoated, newly-applied Stonhard mortars and grouts: GS, HT, UR, UT, TG6, TG8, CR5 and PM5. For questions regarding other possible substrates or an appropriate primer, contact your local Stonhard representative or Technical Service.

## SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service.

## APPLICATION GUIDELINES

For optimal working conditions, substrate temperature must be between 15 to 27°C. Cold areas must be heated until the slab temperature is above 13°C to ensure the material achieves a proper cure. A cold substrate will make the material stiff and difficult to apply. Warm areas or areas in direct sunlight must be shaded or arrangements made to work during evenings or at night. A warm substrate (15 to 27°C) will aid in the material's workability; however, a hot substrate (27 to 37°C) or a substrate directly in the sun will shorten the material's working time and can cause other phenomenon such as pinholing and bubbling. Substrate temperature must be greater than 3°C above dew point during application and curing period.

Application and curing times are dependent upon ambient and surface conditions. Consult Stonhard's Technical Service Department if conditions are not within recommended guidelines.

## PRIMING

Vacuum the substrate before priming and make sure the surface is dry. The use of Stonchem Epoxy Primer is necessary in all applications of Stonchem 626. This ensures maximum product performance. (See the Stonchem Epoxy Primer product sheet for details.)

**Note:** Stonchem Epoxy Primer must be tack-free prior to application of Saturant Base Coat.

## APPLICATION

### Saturant – Basecoat

Mix the amine and resin in a c.a. 20 liter bucket using a heavy-duty, slow-speed drill (400 to 600 rpm) with a Jiffy Mixer for one minute. Pour the saturant onto the substrate and spread out with a squeegee. The saturant should be spread out in a sequence to allow application of the engineering fabric. Do not leave any puddling during this squeegee step. Puddling will lead to over saturation of the engineering fabric.

### Engineering Fabric

Place the engineering fabric on the saturant immediately after it is applied. This is important to achieve maximum wetting. Press the engineering fabric into the saturant with a dry, medium nap roller. Overlap adjacent engineering fabric 13 mm. Immediately apply the saturant.

### Saturant

Mix amine and resin in a c.a. 20 liter bucket using a heavy-duty, slow-speed drill (400 to 600 rpm) with a Jiffy Mixer for one minute. Apply the saturant to the engineering fabric with a saturated medium nap roller. To wet the roller, dip it into the mixing bucket. Always work from the bucket. Do not pour the saturant directly onto the engineering fabric. This will decrease the saturant's coverage. If the air temperature is above 27°C, use of plastic mixing buckets will increase the pot life of the material. The engineering fabric is completely saturated when white strands are no longer present. When the engineering fabric is completely saturated, roll with a ribbed roller to release air pockets in the reinforcement and to help mesh the engineering fabric and saturant together. To saturate the overlaps, roll several times over the length of the overlap with a saturated roller. Then, roll with a ribbed roller several times until the overlap is no longer visible. Allow the saturant and engineering fabric to cure (usually 4 to 6 hours) before proceeding.

### Mortarcoat

Lightly sand the engineering fabric/saturant layer with a sanding disc attachment in areas with protruding fibers. Pre-mix the amine and resin in a c.a. 20 liter mixing bucket with a heavy-duty, slow-speed drill (400 to 600 rpm) with a Jiffy Mixer for one minute. Next, gradually add Mortarcoat aggregate while mixing for an additional 2 minutes. For vertical applications, use Vertical Mortarcoat

## STATIC CONTROL PROPERTIES

Stonchem 626 has been specifically designed to comply with the ANSI/ESD S20.20 specification for the protection of electrical and electronic parts, assemblies and equipment.

Surface Resistance ..... < 1 megohms (ESD-S7.1)

Body Voltage Generation ..... < 100 volts\* (ESD STM97.2)

*\*Body Voltage Generation is not solely a function of flooring conductivity but is a combination of many factors, including footwear and environmental conditions. Your specific environment and choice of footwear may yield slightly different results.*

Electrostatic Discharge (ESD) flooring has a variety of applications from microchip manufacturing to military ordinance. Therefore, each facility may have unique resistance requirements based on their individual ESD programs. It is important to identify the resistance requirements and test method used for each project prior to installing any ESD flooring.

## ELECTRICAL TESTING

Once the conductive mortar layer has cured, it must be tested for proper conductivity. Point-to-point and point-to-ground readings should be taken and all values should fall below  $5.0 \times 10^5$  ohms ( $\Omega$ ).

The floor must also be tested after the carbon-filled topcoat has cured. Once the conductive sealer is tack-free, point-to-point and point-to-ground readings should be taken. All values must fall below  $1.0 \times 10^6$  ohms ( $\Omega$ ).

**Note:** Stonhard tests all floors in accordance with the ESD S7.1 test method. Various other ESD standards and test methods are available and they each have their own unique parameters. Contact the Stonhard's technical service department if you wish to use a different test method.

Do not leave any puddling during this squeegee step. Puddling will lead to over saturation of the engineering fabric.

aggregate. Mixing is complete when no dry clumps of material exist. Pour the material onto the floor and spread out with a 0.4 mm notched squeegee. Backroll the area with a medium nap roller to remove squeegee lines. The material may appear rough at first, but will level out to a smooth finish. For vertical surfaces, use a large steel trowel or knife to pull an initial coat of vertical material onto the wall, then finish smooth with a flat rubber squeegee. Allow the mortarcoat to cure (usually 4-6 hours) before proceeding.

**Note:** If the application requires a conductive system, you must test the mortarcoat layer for conductivity using the megger to ensure it is within the proper range. The conductivity of the mortarcoat layer must be below  $0.5 \times 10^6$  ohms at 100 volts.

#### **Topcoat**

Lightly sand the mortarcoat in areas where protrusions exist. Vacuum the area completely. Mix the amine and resin in a 5 gallon mixing container using a heavy-duty, slow-speed drill (400 to 600 rpm) with a Jiffy Mixer for 2 minutes. Pour the material onto the floor and spread out with a 0.4 mm notched squeegee. Backroll the area with a medium nap roller to remove squeegee lines, using long roll strokes to decrease the visibility of roller lines. For vertical surfaces, pour a bead of material along the base of the wall and, using a medium nap roller, roll the material onto the vertical surface. The wet film thickness of the coating is 250 to 300 microns. Check the thickness with a wet film gauge. If the coating is too thick, the conductivity readings will be affected.

**Note:** If the application requires a conductive system, you must test the finished system for conductivity using the megger to ensure it is within the proper range. The conductivity of the final system must be below 1,000,000 ohms. A static control report detailing the resistance readings over the entire area must be filled out and submitted to the customer.

#### **CURING**

The surface of Stonchem 626 will be tack-free in 4 to 6 hours at 21°C. The coated area may be put back in service in 24 hours at 21°C. Ultimate physical characteristics will be achieved in 7 days.

#### **PRECAUTIONS**

- Avoid contact with Stonchem 620 amine and resin, as they may cause skin, respiratory and eye irritation.
- Acetone is recommended for clean up of Stonchem 600 amine and resin material spills. Use this material only in strict accordance with the manufacturer's recommended safety procedures. Dispose of waste materials in accordance with government regulations.
- The use of NIOSH/MSHA approved respirators using an organic vapor/acid gas cartridge is recommended.
- The selection of proper protective clothing and equipment will significantly reduce the risk of injury. Body covering apparel, safety goggles and impermeable nitrile gloves are highly recommended.
- In case of contact, flush the area with copious amounts of water for 15 minutes and seek medical attention. Wash skin with soap and water.
- If material is ingested, immediately contact a physician. **DO NOT INDUCE VOMITING.**
- Use only with adequate ventilation.

#### **NOTES**

- Safety Data Sheets for Stonchem 626 are available online at [www.stonhard.com](http://www.stonhard.com) under Products or upon request.
- Specific information regarding chemical resistance is available in the Stonchem 600 Series Chemical Resistance Guide.
- A staff of technical service engineers is available to assist with product application or to answer questions related to Stonhard products.
- Requests for technical literature or service can be made through local sales representatives and offices, or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic and cleaning. Generally, high-gloss coatings are subject to a reduction in gloss, while matte-finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant buildup occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction-enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.

**CE MARKING**

The harmonized European Standard EN 1504-2 „Products and systems for the protection and repair of concrete structures – Definitions, requirements, quality control and evaluation of conformity – Part 2: Surface protection systems for concrete” gives specifications for products and systems based on methods “hydrophobic impregnation”, “impregnation” and “coating” for the various principles presented under EN 1504-9.

Products which fall under this specification have to be CE labelled as per Annex ZA. 1, Tables ZA1a to ZA 1g according to the scope and relevant clauses there indicated, and fulfill the requirements of the given mandate of the Construction Products Regulation nr. 305/2011. For flooring systems not dedicated to protect or reinstate the integrity of a concrete structure, EN 13813 applies. Products acc. EN 1504- 2 used as flooring systems with mechanical loads also must fulfil EN 13813. Here below indicated are the performance classes achieve according to the standard. For the specific performance results of the product to the particular tests, please see the actual values above in the PDS.


Stoncor Europe Rue du Travail 9 1400 Nivelles, Belgium 22
DOP.626.2022.23.03  EN 1504-2
Surface Protection Product Ingress Protection 1.3(C) Physical Resistance 5.1(C)
Cap. Absorption & Permeability to Water Vapor.....W<0.1 kg/m <sup>2</sup> *h <sup>0.5</sup> Water Permeability .....Class III Permeability to CO <sup>2</sup> .....S <sub>d</sub> >50m Adhesion Strength by Pull-Off Test .....>2.0 MPa Fire Resistance .....B <sub>f</sub> -s1 Abrasion Resistance.....<3000mg, H-22 Impact Resistance .....Class III

**IMPORTANT:**

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

Rev.03/22  
© 2022 Stonhard www.stonhard.com



**European Offices:**

Belgium	+32 674 93 710	Spain	+34 933 623 785	Germany	+49 240 541 740
France	+33 160 064 419	Portugal	+351 227 535 642	The Netherlands	+31 165 585 200
Poland	+48 422 112 768	United Kindom	+44 1925 649 458	Italy	+39 022 53 751
		East Europe	+48 422 112 768		